








Indicative Technical Specifications*

	TEST	TEST METHOD	TEST RESULT
	Impact Resistance	TS EN 14617 -9	min. 2 Joule for 1,2 cm thickness min. 3 Joule for 2 cm thickness
	Flexural Strength	TS EN 14617-2	40-70 N/mm ²
	Abrasion Resistance	TS EN 14617 -4	Max. 30 mm
	Water Absorption	TS EN 14617-1	Max. %0,1
	Reaction to Fire	TS EN 13501-1	A2 fl, S1

* Test results may vary according to product properties.